

EUNIGROUT 500 HD

CEMENTITIOUS NON-SHRINK GROUT

DESCRIPTION

EUNIGROUT 500 HD is a premixed powdered grout made from strong cement, graded aggregates, and special additives to enhance strength. When combined with water, it becomes a fluid grout that doesn't separate and can effectively fill complex spaces. It's suitable for various grouting needs where minimizing shrinkage is important.

USES

EUNIGROUT 500 HD is a versatile grouting solution suitable for a wide range of applications:

- Concrete and earth water retaining structures
- Concrete dams, water spillways and underwater grouting
- Under-plate grouting, space grouting
- Repairs to precast concrete
- Bedding bearing plates
- Anchor bolt fixing
- Cable grouts and crane rail assembly

ADVANTAGES

- Non-gaseous grout, free of bleeding with long stability over a wide range of temperatures and humidities
- Could be factory- or site-blended
- Extremely fluid consistency for easy application in difficult access areas
- Excellent flow retention and long usable life, even at high ambient temperatures
- Non-shrinkage characteristics

APPLICATION

Surface Preparation

Prior to application, it is important to ensure that all surfaces are clean and in good condition. Remove any surface laitance by using acid etching or grinding methods. It is recommended to thoroughly wet all surfaces 6 - 24 hours before starting the application and maintain a moist condition during the placing process. Any excess surface water should be removed prior to applying the product.

TYPICAL PROPERTIES

Appearance	Dark Grey
Fresh Wet Density	2.32 Kg/L
Compressive Strength (BS 6319, Part 2), @ 30°C	≥ 48MPa @ 7 days ≥ 60 MPa @ 28 days
Application Thickness	20 mm - 60 mm
Application Temperature	5 -35 °C

MIXING

For optimum dispersion and workability, it is recommended to use mechanical grout mixers. Conventional or hand mixing may lead to lower workability. Start by mixing the dry powder and gradually add the water with a ratio of (3 - 4 liters) over a span of 1 - 2 minutes. Continue mixing for an additional 2 - 3 minutes until the mixture is smooth and cohesive. It is advisable to maintain consistent timings for each operation to achieve consistent results whenever possible.

Application Instructions

1. Under-plate grouting

When performing underplate grouting, it is recommended to use a flowing or fluid consistency grout. Before starting to mix the grout ensure that the form-work is properly sealed to prevent grout leakage. Sufficient material should be available to complete the entire task and achieve a continuous fill.

It's important to pour the grout from one side only so as to avoid air entrapment. Make sure not to vibrate the grout, but rods, straps and chains can be used to assist the complete filling. It is important to note that the compressive strength development and ultimate strength of the concrete may be slightly reduced compared to flowing grouts. It is important to note that the compressive strength development and ultimate strength of the concrete may be slightly reduced compared to flowing grouts.

2. Pumping

EUNIGROUT 500 HD can be effectively pumped using grout pumps equipped with ball valves, such as piston, ram or diaphragm pumps.

CURING

Good curing is crucial for all exposed surfaces, especially in dry and sunny conditions. Neglecting proper curing can result in reduced bond, strength and durability. Various methods of curing can be employed, including water ponding, mist spraying and wet hessian, among others. Regardless of the method used, it is important to maintain the curing process for a minimum of 7 days. In hot climatic conditions, extra attention should be given to curing in order to achieve optimal properties and extend the service life of the structure.

YIELD

EUNIGROUT 500 HD Approximately 12 - 13 litres per 25Kg bag.

PACKAGING

EUNIGROUT 500 HD is supplied in 25 kg bags.

STORAGE

EUNIGROUT 500 HD should be stored and maintained in dry and cool conditions at temperatures between 2°C and 40°C. The shelf life of EUNIGROUT 500 HD is 12 months from the date of production.

HEALTH AND SAFETY

For more information, please check the Material Safety Data Sheet.

CONTACT

Al-Faiha for Engineering Products is the exclusive licensee manufacturer for ECA.

For more information, please contact us at techsupport@alfaihaengineering.com.

DISCLAIMER

ECA aims to ensure the accuracy of information and recommendations in the product literature. However, due to variations in materials, substrates, and site conditions, and without control over product application, storage, weather, and usage conditions, ECA cannot be held liable for any resulting issues.